



#### AVERAGE COMPOSITION

in the outside surface of a sheet

	Symbol	<b>NCAx</b>
Aluminum	Al	8 ... 12%
Carbon	C	< 0.1%
Chromium	Cr	15 ... 20%
Copper	Cu	-
Iron	Fe	4 ... 5%
Molybdenum	Mo	-
Manganese	Mn	0.2%
Nickel	Ni	60 ... 65%
Phosphor	P	

**RECEMAT BV | De Vlasman 2C | 6669ND Dodewaard | The Netherlands | [www.recemat.nl](http://www.recemat.nl)**

version APRIL 2015

no rights can be derived from these figures