

DATA SHEET NICKEL-CHROMIUM-EXTRA FOAM

Designation	NCX0610	NCX1116	NCX1723	NCX2733	NCX4753
Grade = number of pores / inch ppi	6 ... 10	11 ... 16	17 ... 23	27 ... 33	47 ... 53
Estimated average pore diam. mm	2.3	1.4	0.9	0.6	0.4
Density average gr/cm ³	0.5 ... 0.9	0.5 ... 0.9	0.5 ... 0.9	0.5 ... 0.9	0.5 ... 1.3
Relative density (average)	8%	8%	8%	8%	10%
Porosity (100% - rel. density)	92%	92%	92%	92%	90%
Specific Surface m ² /m ³	500	1000	1600	2800	5400
Sheet length mm	900	900	900	900	900
Sheet width mm	600	600	600	600/500	600/500

AVERAGE COMPOSITION

in the outside surface of a sheet

	Symbol	
Aluminum	Al	-
Carbon	C	< 0.1%
Chromium	Cr	30...45 %
Copper	Cu	0.3%
Iron	Fe	5%
Molybdenum	Mo	< 0.1%
Manganese	Mn	< 0.1%
Nickel	Ni	Balance 49 ... 64%
Phosphor	P	< 0.1%